

TOP GLOVE

TOP QUALITY, TOP EFFICIENCY

THE WORLD'S LARGEST MANUFACTURER OF GLOVES

LATEX FITTED EXAMINATION GLOVES

POWDERED & POWDER-FREE



Scan for Latex Fitted Examination Gloves



Functional Benefits

- Provides superior comfort
- Hand specific features which help reduce fatigue
- Greater protection

Recommended for:



Medical examination and procedures



Suitable for use with PPE gown



LATEX FITTED EXAMINATION GLOVES

LATEX FITTED EXAMINATION GLOVES

POWDERED & POWDER-FREE

QUALITY STANDARD

Conforms to EN455, ASTM D3578 and ISO 11193 Standard

GLOVE SIZES

- 6.0 (XS), 6.5 (S), 7.5 (M), 8.5 (L), 9.0 (XL)
- Size of gloves shall be marked in the check box on the shipping carton with black ink

PRODUCT SPECIFICATION

Type	: Latex Fitted Examination Glove, Powdered, Powder Free, Non-Sterile
Material	: Natural High Grade Rubber Latex
Colour	: Natural
Design & Features	: Powdered: Hand specific, curved fingers, palm textured surface, beaded cuff, USP grade absorbable cornstarch Powder-Free: Hand specific, curved fingers, palm textured surface, beaded cuff, polymer coated
Storage	: The gloves shall maintain their properties when stored in a dry condition. Avoid direct sunlight
Packing Style	: 50 pcs gloves (Left); 50 pcs gloves (Right) per dispenser, 10 dispensers x 1 carton
Shelf-life	: 5 years from the date of manufacture



PHYSICAL DIMENSION

Weight Standard	TOP GLOVE			MAXITEX		
	EN455	ASTM D3578	ISO 11193	EN455	ASTM D3578	ISO 11193
Dimensions						
Glove Length (mm)	Min 280					
Thickness						
6.0 (XS)	77 +/- 5					
6.5 (S)	83 +/- 5					
7.5 (M)	95 +/- 5					
8.5 (L)	109 +/- 5					
9.0 (XL)	115 +/- 5					
Thickness All Sizes (mm) *Single Wall						
Finger	0.17 +/- 0.02			0.23 +/- 0.02		
Palm	0.15 +/- 0.02			0.19 +/- 0.02		
Cuff	0.13 +/- 0.02			0.14 +/- 0.02		

PHYSICAL PROPERTIES

Weight Property	TOP GLOVE & MAXITEX		
	EN455	ASTM D3578	ISO 11193
Elongation at Break (%)			
Before Aging	N/A	Min 650	Min 650
After Aging	N/A	Min 500	Min 500
Tensile Strength (MPa)			
Before Aging	N/A	Min 18	N/A
After Aging	N/A	Min 14	N/A
Median Force at Break (N)			
Before Aging	Min 6	N/A	Min 7
After Aging	Min 6	N/A	Min 6

If you have any enquiries on our product, please contact:

TOP GLOVE SALES & CORPORATE OFFICE

Level 21, Top Glove Tower,
16, Persiaran Setia Dagang,
Setia Alam, Seksyen U13,
40170 Shah Alam,
Selangor D.E., Malaysia



Top Glove Website